

Recommended Cutting Angles Per Wood Species

Information below should be used as a guideline - results may vary

Wood Species	Kiln Dried Wood Cutting Angle
Ash	10°
Basswood	10°
Beech	10°
Birch	10°
Cedar	20°
Cherry	10°
Chestnut	5°
Cottonwood	20°
Cypress	5°
Elm, Hard	0°
Elm, Soft	5°
Fir	15°
Gum	20°
Hemlock	15°
Hickory	5°
Mahogany	10°
Maple, Hard	5°
Maple, Soft	20°
Oak, Red	10°
Oak, White	5°
Oak Qtd.	10°
Pine, Yellow	20°
Pine, White	10°
Pine, Ponderosa	20°
Poplar	20°
Redwood	5°
Spruce	20°
Sycamore	5°
Walnut	5°